

# INDION° 220 Na

# Description

INDION 220 Na is a high capacity strongly acidic cation exchanger in bead form. It is based on cross linked polystyrene and has a gel structure. The resin contains sulphonic acid functional groups. It is supplied moist in the sodium form.

# **Applications**

INDION 220 Na is used most widely in sodium form for water softening application. It can be used also in twostage de - ionising as the cation exchanger in the hydrogen cycle.

# **Characteristics**

Appearance	:	Moist golden yellow beads
Matrix	:	Styrene divinylbenzene copolymer
Functional Group	:	Sulphonic acid
lonic form as supplied	:	Sodium
Total exchange capacity	:	1.8 meq/ml, minimum
Moisture holding capacity	:	50 - 55%
Shipping weight *	:	810 kg/m³, approximately
Particle size range	:	0.3 to 1.2 mm
> 1.2 mm	:	5.0%, maximum
< 0.3 mm	:	1.0%, maximum
Uniformity co - efficient	:	1.7, maximum
Effective size	:	0.45 to 0.55 mm
Maximum operating temperature	:	140°C
Operating pH range	:	0 to 14
Volume change	:	Na to H, 8% approximately
Resistance to reducing agents	:	Good
Resistance to oxidizing agents	:	Generally good, chlorine should be absent

<sup>6</sup> Weight of resin, as supplied, occupying 1 m<sup>3</sup> in a unit after backwashing and draining.

## Packing

HDPE Lined bags	25/ 50 lts	LDPE bags 1 cft	/ 25 lts
Super sack	1000 lts	Super sack	35 cft
MS drums	Fiber drums		
with liner bags	180 lts	with liner bags 7 cfl	

## Storage

Ion exchange resins require proper care at all times. The resin must never be allowed to become dry. Regularly open the plastic bags and check the condition of the resin when in storage. If not moist, add enough clean demineralised water and keep it in completely moist condition. Always keep the resin drum in the shade. Recommended storage temperature is between 20°C and 40°C.

### Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

**INDION**" is the registered trademark of Ion Exchange (India) Ltd.



#### CORPORATE OFFICE

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011 Tel: 022-3989 0909 Fax: 022-2493 8737 E-mail: ieil@ionexchange.co.in

#### INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 701 Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918 E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

#### **REGIONAL OFFICES**

• Chennai	- Tel: 044-3989 0909/3910 2900 E-mail: checro@ionexchange.co.in	Fax: 044-2815 3361
• Delhi	- Tel: 011-3989 0909/3054 3200 E-mail: delcro@ionexchange.co.in	Fax: 011-2577 4837
• Kolkata	- Tel: 033-3989 0909/3043 3400 E-mail: calcro@ionexchange.co.in	Fax: 033-2400 4345
• Vashi	- Tel: 022-3989 0909/3913 2300 E-mail: mumcro@ionexchange.co.i	Fax: 022-2788 9839 n

#### BRANCH OFFICES

• Bengaluru	Bengaluru <sup>-</sup> Tel: 080-2204 2888 E-mail: bngcro@ionexchange.co.in			
• Bhubaneswar	- Tel: 0674-326 9525 E-mail: bbsr@ionexchange.co.in			
• Chandigarh	- Tel: 0172-274 5011 E-mail: delcro@ionexchange.c	Fax: 0172-274 4594 to.in		
• Hyderabad	- Tel: 040-3066 3101/02/03 E-mail: hydcro@ionexchange.			
• Lucknow	- Tel: 0522-301 3401/02 E-mail: luk.general@ionexcha			
• Vadodara	- Tel: 0265-302 7489/90 E-mail: brdcro@ionexchange.			
• Visakhapatnam	- Tel: 0891-324 6253 E-mail: sales.vizag@ionexchar	nge.co.in		
FACTORIES : Ankleshwar • Hosur • Patancheru • Rabale • Verna ALL INDIA SERVICE AND DEALER NETWORK				